

## AMENDMENTS TO THE CLAIMS

*A listing of the claims presented in this patent application appears below. This listing replaces all prior versions and listing of claims in this patent application.*

**Claim 1 (currently amended):** A heat resisting martensitic steel comprising, by weight, 0.05 to 0.30% C, not more than 0.50% Si,  $[[0.5]]$  0.05 to 0.60% Mn, 8.0 to 13.0% Cr, 0.5 to 3.0% Ni, 1.0 to 3.0% Mo, 0.1 to 1.5% tungsten (W), 0.5 to 4% Co, 0.05 to 0.35% vanadium (V), 0.02 to 0.30% in total of one or two elements selected from the group consisting of Nb and Ta, and 0.02 to 0.10% nitrogen (N), wherein

a value of the square of a difference between the Ni amount and the Co amount, and the Ni amount are not more than values determined by a straight line drawn on a point A (1.0, 2.7%) and a point B (2.5, 1.0%) in the orthogonal coordinates shown in the attached drawing of Fig. 2 which represents a relationship between the above square value and the Ni amount, where the square value does not exceed 1.8, and

wherein an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$  is not less than 0.75.

**Claim 2 (canceled).**

**Claim 3 (original):** A heat resisting martensitic steel according to claim 1, which further comprises, by weight, not more than 1.5% Re, and 0.001 to 0.015% boron (B).

**Claims 4-7 (canceled).**

**Claim 8 (original):** A heat resisting martensitic steel according to claim 1, which further comprises, by weight, at least one of not more than 0.5% Cu, not more than 0.5% Ti, not more than 0.2% Al, not more than 0.1% Zr, not more than 0.1% Hf, not more than 0.01% Ca, not more than 0.01% Mg, not more than 0.01% yttrium (Y), and not more than 0.01% of a rare earth element.

**Claim 9 (canceled).**

**Claim 10 (withdrawn):** A gas turbine comprising:

- a turbine stub shaft;
- a plurality of turbine discs connected to the turbine stub shaft by turbine stacking bolts via turbine spacers;
- turbine blades each implanted in the respective disc to rotate by high-temperature combustion gas generated in a combustion device;
- a distant piece connected to the turbine discs;
- a plurality of compressor rotors connected to the distant piece;
- compressor blades which are implanted to compressor discs constituting the respective compressor rotor, and which compress air; and
- a compressor stub shaft connected to the compressor rotors, wherein
  - at least one of the turbine discs, the distant piece, the turbine spacers, the compressor disc at a last stage, and the turbine stacking bolts is made of a martensitic steel comprising, by weight, 0.05 to 0.30% C, not more than 0.50% Si, not more than 0.60% Mn, 8.0 to 13.0% Cr, 0.5 to 3.0% Ni, 1.0 to 3.0% Mo, 0.1 to 1.5% W, 0.5 to 4% Co, 0.05 to 0.35% vanadium (V), 0.02 to 0.30% in total of one or two elements selected from the group consisting of Nb and Ta, and 0.02 to 0.10% nitrogen (N), wherein
    - a value of the square of a difference between the Ni amount and the Co amount, and the Ni amount are not more than values determined by a straight line drawn on a point A (1.0, 2.7%) and a point B (2.5, 1.0%) in the orthogonal coordinates shown in the attached drawing of Fig. 2 which represents a relationship between the above square value and the Ni amount, and an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$  is not less than 0.5; or
    - an amount ratio of  $\text{W}/\text{Mo}$ , and the Mn amount are not more than values determined by a straight line drawn on a point C (1.3, 0.15%) and a point D (2.5, 0.37%) in the orthogonal coordinates shown in the attached drawing of Fig. 4 which represents a relationship between the amount ratio and the Mn amount; or

an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$ , and the Mn amount are not less than values determined by a straight line drawn on a point E (0.25, 0.4%) and a point F (0.7, 0.15%) in the orthogonal coordinates shown in the attached drawing of Fig. 6 which represents a relationship between the amount ratio and the Mn amount.

**Claim 11 (withdrawn):** A disc for a gas turbine, which is a disc member comprising a circumferential implanting section for a turbine blade, and a plurality of bores receiving a plurality of stacking bolts by which a plurality of the disc members are integrally fastened to one another, wherein

the disc is made of a martensitic steel comprising, by weight, 0.05 to 0.30% C, not more than 0.50% Si, not more than 0.60% Mn, 8.0 to 13.0% Cr, 0.5 to 3.0% Ni, 1.0 to 3.0% Mo, 0.1 to 1.5% tungsten (W), 0.5 to 4% Co, 0.05 to 0.35% vanadium (V), 0.02 to 0.30% in total of one or two elements selected from the group consisting of Nb and Ta, and 0.02 to 0.10% nitrogen (N), wherein

a value of the square of a difference between the Ni amount and the Co amount, and the Ni amount are not more than values determined by a straight line drawn on a point A (1.0, 2.7%) and a point B (2.5, 1.0%) in the orthogonal coordinates shown in the attached drawing of Fig. 2 which represents a relationship between the above square value and the Ni amount, and an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$  is not less than 0.5; or

an amount ratio of  $\text{W}/\text{Mo}$ , and the Mn amount are not more than values determined by a straight line drawn on a point C (1.3, 0.15%) and a point D (2.5, 0.37%) in the orthogonal coordinates shown in the attached drawing of Fig. 4 which represents a relationship between the amount ratio and the Mn amount; or

an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$ , and the Mn amount are not less than values determined by a straight line drawn on a point E (0.25, 0.4%) and a point F (0.7, 0.15%) in the orthogonal coordinates shown in the attached drawing of Fig. 6 which represents a relationship between the amount ratio and the Mn amount.

**Claim 12 (withdrawn):** A gas turbine distant piece which is a cylindrical member comprising protrusions provided at both opposite ends of the cylindrical member; a plurality of bores in one of the protrusions, which receive a plurality of stacking bolts by which the cylindrical member is integrally fastened to turbine discs, and a plurality of other bores in the other protrusion, which receive a plurality of other stacking bolts by which the cylindrical member is integrally fastened to compressor discs, wherein the gas turbine distant piece is made of a martensitic steel comprising, by weight, 0.05 to 0.30% C, not more than 0.50% Si, not more than 0.60% Mn, 8.0 to 13.0% Cr, 0.5 to 3.0% Ni, 1.0 to 3.0% Mo, 0.1 to 1.5% tungsten (W), 0.5 to 4% Co, 0.05 to 0.35% vanadium (V), 0.02 to 0.30% in total of one or two elements selected from the group consisting of Nb and Ta, and 0.02 to 0.10% nitrogen (N), and wherein

a value of the square of a difference between the Ni amount and the Co amount, and the Ni amount are not more than values determined by a straight line drawn on a point A (1.0, 2.7%) and a point B (2.5, 1.0%) in the orthogonal coordinates shown in the attached drawing of Fig. 2 which represents a relationship between the above square value and the Ni amount, and an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$  is not less than 0.5; or

an amount ratio of  $\text{W}/\text{Mo}$ , and the Mn amount are not more than values determined by a straight line drawn on a point C (1.3, 0.15%) and a point D (2.5, 0.37%) in the orthogonal coordinates shown in the attached drawing of Fig. 4 which represents a relationship between the amount ratio and the Mn amount; or

an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$ , and the Mn amount are not less than values determined by a straight line drawn on a point E (0.25, 0.4%) and a point F (0.7, 0.15%) in the orthogonal coordinates shown in the attached drawing of Fig. 6 which represents a relationship between the amount ratio and the Mn amount.

**Claim 13 (withdrawn):** A gas turbine compressor disc which is a disc member comprising

a circumferential implanting section for a compressor blade, and a plurality of bores receiving a plurality of stacking bolts by which a plurality of the disc members are integrally fastened to one another, wherein the gas turbine compressor disc is made of a martensitic steel

Application No.: 10/757,847

comprising, by weight, 0.05 to 0.30% C, not more than 0.50% Si, not more than 0.60% Mn, 8.0 to 13.0% Cr, 0.5 to 3.0% Ni, 1.0 to 3.0% Mo, 0.1 to 1.5% tungsten (W), 0.5 to 4% Co, 0.05 to 0.35% vanadium (V), 0.02 to 0.30% in total of one or two elements selected from the group consisting of Nb and Ta, and 0.02 to 0.10% nitrogen (N), and wherein

a value of the square of a difference between the Ni amount and the Co amount, and the Ni amount are not more than values determined by a straight line drawn on a point A (1.0, 2.7%) and a point B (2.5, 1.0%) in the orthogonal coordinates shown in the attached drawing of Fig. 2 which represents a relationship between the above square value and the Ni amount, and an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$  is not less than 0.5; or

an amount ratio of  $\text{W}/\text{Mo}$ , and the Mn amount are not more than values determined by a straight line drawn on a point C (1.3, 0.15%) and a point D (2.5, 0.37%) in the orthogonal coordinates shown in the attached drawing of Fig. 4 which represents a relationship between the amount ratio and the Mn amount; or

an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$ , and the Mn amount are not less than values determined by a straight line drawn on a point E (0.25, 0.4%) and a point F (0.7, 0.15%) in the orthogonal coordinates shown in the attached drawing of Fig. 6 which represents a relationship between the amount ratio and the Mn amount.

**Claim 14 (withdrawn):** A gas turbine stacking bolt which is a bar member comprising a screw portion at one end thereof, and a polygonal head portion at the other end, wherein the gas turbine stacking bolt is made of a martensitic steel comprising, by weight, 0.05 to 0.30% C, not more than 0.50% Si, not more than 0.60% Mn, 8.0 to 13.0% Cr, 0.5 to 3.0% Ni, 1.0 to 3.0% Mo, 0.1 to 1.5% tungsten (W), 0.5 to 4% Co, 0.05 to 0.35% vanadium (V), 0.02 to 0.30% in total of one or two elements selected from the group consisting of Nb and Ta, and 0.02 to 0.10% nitrogen (N), and wherein

a value of the square of a difference between the Ni amount and the Co amount, and the Ni amount are not more than values determined by a straight line drawn on a point A (1.0, 2.7%) and a point B (2.5, 1.0%) in the orthogonal coordinates shown in the attached drawing of Fig. 2

Application No.: 10/757,847

which represents a relationship between the above square value and the Ni amount, and an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$  is not less than 0.5; or

an amount ratio of  $\text{W}/\text{Mo}$ , and the Mn amount are not more than values determined by a straight line drawn on a point C (1.3, 0.15%) and a point D (2.5, 0.37%) in the orthogonal coordinates shown in the attached drawing of Fig. 4 which represents a relationship between the amount ratio and the Mn amount; or

an amount ratio of  $\text{Mo}/(\text{Mo} + 0.5\text{W})$ , and the Mn amount are not less than values determined by a straight line drawn on a point E (0.25, 0.4%) and a point F (0.7, 0.15%) in the orthogonal coordinates shown in the attached drawing of Fig. 6 which represents a relationship between the amount ratio and the Mn amount.